



IN THE SPECIFICATION

Please replace the paragraph at page 2, lines 33-37, with the following rewritten paragraph:

- providing a flexible sheet derived from at least one plate obtained by the technique of casting a strip by silkscreen printing from a viscous material made of a binder and a metal powder of a superalloy in a brazing binder;

Please replace the paragraph at page 3, lines 6-11, with the following rewritten paragraph:

- raising the assembly to a temperature higher than the melting temperature of the brazing binder but lower than the melting temperature of said metal powder so as to form a coating by establishing a bond between said preform and said face to be protected of a metal substrate and/or article.